

# CHEM-ROCK ULTRA UV

**100% SOLID UV RESISTANT EPOXY**

**DESCRIPTION :**

**CHEM-ROCK ULTRA UV** is a NEW generation of epoxy that exhibits 'Ultimate' color and gloss retention even in exterior applications. **CHEM-ROCK ULTRA UV** is a 2-component, 100% solids material designed to protect decorative floor and walls systems from premature yellowing and loss of gloss. **CHEM-ROCK ULTRA UV** resists yellowing and loss of gloss due to UV exposure, exhibits good resistance to most common chemicals, and meets all USDA guidelines for use in federally inspected facilities.

**USES :**

**CHEM-ROCK ULTRA UV** provides long-lasting UV protection and non-yellowing characteristics as a topcoat coat for most ROCK-TRED floor or wall coating systems. This unique material has extended working and cure times that allow for ease of application even in warmer temperatures.

**TYPICAL COVERAGE:**

**CHEM-ROCK ULTRA UV** can be applied as a 'smooth' coating or applied over a broadcast surface from 160 sq. ft. / gal. (10 mils).

**[NOTE : When adding colorant to ULTRA UV – application at 16 mils (100 sq. ft. / gal.) may be required for adequate 'hide' over a clear or dark colored primer or basecoat material].**

**ADVANTAGES :**

- Ultimate non-yellowing
- Ultimate gloss retention
- Extended working time
- No odor
- Easy mix ratio
- 100% solids

**TYPICAL PROPERTIES :**

APPLICATION PROPERTIES	
Volume mix ratio	2:1 (Resin to Hardener)
Viscosity (mixed)	600 - 900 CPS Typical
Solids Content (%)	100% (ASTM D-2697)
Hardness (ASTM D-2240)	70 - 75 (Shore D)
VOC	0 g/l (EPA method 24)
Application Temps.	65 <sup>o</sup> - 90 <sup>o</sup> F (10 <sup>o</sup> - 29 <sup>o</sup> C)
Pot Life	27 - 40 minutes @ 75 <sup>o</sup> F (24 <sup>o</sup> C)
Time to Dry (recoat)	2 - 4 hours @ 75 <sup>o</sup> F (24 <sup>o</sup> C)
Time to Cure (foot traffic)	4 - 6 hours @ 75 <sup>o</sup> F (24 <sup>o</sup> C)
Shelf Life	1 Year in unopened containers

*For physical properties on this product, refer to ROCK-TRED's Data Chart*

**PACKAGING :**

- 1.5 Gallon Units (5.7 L) BAG-PAK™
- 3 Gallon Units (11.4 L) BAG-PAK™
- 15 Gallon Units (57 L) – in 3-5 gal. pails

# CHEM-ROCK ULTRA UV

## LIMITATIONS & FOR BEST RESULTS :

- Do not thin this product.
- Do not apply when temperature will falls below 5 degrees above dew point for duration of cure.
- Do not allow to puddle during application.
- Allow each coat to dry to 'tack-free' or clear prior to re-coat.
- When re-coating, always apply the next coat within 24 hours of completing the previous coat.

## PRODUCT APPLICATION :

Apply by brush, roller or squeegee. ROCK-TRED product test data is based on environmental temperatures of 75<sup>0</sup> F (24<sup>0</sup> C). Viscosity and working time are always affected by temperatures above or below that mark. When applying product – **always consider the ambient, surface, and product temperature at the time and place of installation.**

## COLOR AND TEXTURES :

**CHEM-ROCK ULTRA UV** is available in clear or can be 'field' pigmented using RTE Colorants. Most ROCK-TRED products are available in a wide range of textures using an appropriate aggregate.

## CHEMICAL RESISTANCE :

Always refer to ROCK-TRED's chemical resistant chart for specific information on each product / system or contact ROCK-TRED directly.

## PRODUCT STORAGE :

**DO NOT** allow ROCK-TRED products to freeze. All ROCK-TRED products should be properly stored above the floor on pallets or shelves, and in an area that has a constant minimum temperature of 50<sup>0</sup> F (10<sup>0</sup> C).

**SURFACE PREPARTION :** Always apply ROCK-TRED products to a 'clean / sound' substrate that is free of laitance, grease, oils, debris, and curing compounds. Concrete substrates should be cured for a minimum of 28 days prior to application of product [except as otherwise noted on the individual Product Data Sheet]. Whenever possible, remove existing coatings and/or flooring systems completely; if complete removal is unavoidable always perform tests to determine adhesion and compatibility to the existing substrate. Surface preparation by means of a shot-blasting machine is the best and recommended method for attaining the desired profile. If the substrate is not properly prepared and the appropriate profile is not achieved, failure of the product to adhere to the substrate may occur.

## CLEAN UP :

Application tools and equipment can be cleaned with Xylene.

## DISPOSAL :

Product containers will contain product residue and must be disposed of properly. Label warnings must be observed at all times. All containers must be disposed in accordance with federal, state, and local regulations.

## IMPORTANT NOTICE :

Always read and acquaint yourself with ROCK-TRED'S Product Data Sheet, MSDS [material safety data sheet], and product labels for each individual product prior to mixing and prior to use. For further assistance, product questions, additional information and/or unexpected or unusual installation conditions – contact your local representative or ROCK-TRED directly for recommendations.

## WARRANTY :

Information about ROCK-TRED products is given, to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you make your own tests to determine suitability of the product for the particular purpose. As products are often applied or used under conditions beyond our control, ROCK-TRED cannot guarantee anything except the quality of its products. ROCK-TRED warrants that the products meet the specifications set forth by ROCK-TRED, but we reserve the right to change any given specification prior to notice. ROCK-TRED DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of a ROCK-TRED product constitutes acceptance of the terms of this limited warranty and the terms and conditions set out in our invoice, contrary provisions of buyer's purchase documents notwithstanding. Upon receipt of the merchandise, purchaser has 30 days to notify ROCK-TRED, in writing, that materials are defective. In the event ROCK-TRED finds that the product delivered is off specification, ROCK-TRED will, at its sole discretion, either replace the product(s) or refund the purchase price thereof, and ROCK-TRED's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of ROCK-TRED exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. ROCK-TRED will, under no circumstances, be liable for special, incidental, or consequential damages. This warranty supersedes all other guaranties, whether oral or written, and whether expressed, implied, or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using, please read the Material Safety Data Sheet and follow all precautions to prevent bodily harm.