

**Product Description:**

**CHEM-ROCK LT-25** is a slightly amber / clear, 100% solids, medium viscosity, 2-component epoxy coating designed for low temperature curing down to 25°F. **CHEM-ROCK LT-25** is a multi-use primer/body/binder epoxy that can be used as a clear or solid color coating or binder for trowel down systems.

**CHEM-ROCK LT-25** is used when an amber/clear or solid color high build coating or trowel down system is required in a low temp environment down to 25°F. Its adhesion promoters and lower viscosity characteristics make it an ideal primer or “seed” coating to broadcast flakes or aggregate into. **CHEM-ROCK LT-25** is VOC compliant and meets all USDA/FDA guidelines for use in federally inspected facilities.

**Physical Testing Information:**

Volume mix ratio	2 to 1 (Resin to Hardener)
Viscosity (mixed)	800 CPS Typical
Solids Content (%)	100 % (ASTM D-2697)
Hardness (ASTM D-2240)	75-85 (Shore D)
VOC	0 g/l (EPA method 24)
Application Temps	20° – 35°F
Gel Time	2 - 6 minutes @ 75°F
Dry to Touch (recoat with compatible materials)	30 - 60 minutes @ 75°F 2.0 hours @ 45°F
Through-Cure	2 - 3 hours @ 75°F 6.5 hours @ 45°F
Open to light traffic	24 hours @ 75°F
Shelf Life:	1 Year in unopened units

Please review ROCK-TRED's Product Data Sheet and SDS for further information on this product. All physical testing information is from performance testing run on neat coats of the tested product unless otherwise indicated.