

ELASTI-THANE BASECOAT

ALIPHATIC ELASTOMERIC POLYURETHANE BASECOAT

DESCRIPTION:

ELASTI-THANE BASECOAT is a high solids, 2-component, aliphatic polyurethane designed to perform multiple functions. It provides the benefits of UV stability with the ability to be extended to almost any thickness when incorporating Rock Tred aggregates and fillers.

USES:

ELASTI-THANE BASECOAT can be used as a stand alone flexible grout or as the base coat for Rock Tred foot traffic membrane systems for use in mechanical equipment rooms, mezzanines, porches and walkways, etc. **ELASTI-THANE BASECOAT** can be left as the finish coat or can be top coated with ELASTI-THANE TOPCOATS for added protection and beauty.

TYPICAL COVERAGE:

ELASTI-THANE BASECOAT can be installed as a grout up to 2 inches or as a high build component in flexible foot traffic membrane systems from 20 to 250 mils.

ADVANTAGES:

ELASTI-THANE BASECOAT is available in gray, black, or white and can be extended (at 1:1 by volume) with Rock Tred Aggregates and fillers.

- 2-component / low odor
- Excellent weathering
- Can be applied in sunlight
- Low VOC's
- Excellent abrasion resistance
- Cures down to 33^o F

TYPICAL PROPERTIES:

APPLICATION PROPERTIES	
Volume mix ratio	Mix entire content of kit
Viscosity [mixed]	4000-6000 CPS Typical
Solids Content [%]	96 % [ASTM D-2697]
Ultimate Elongation (ASTM D412)	1,000-1,200 %
Abrasion Resistance Tabor 1000 cycles / CS 17 wheel / 100g	0.02 grams Loss
Tensile Strength (ASTM D412)	700-800 psi
Hardness (ASTM C-661)	60-65 (Shore A)
Application Temps.	33 ^o – 80 ^o F
Potlife	35-40 minutes @ 75 ^o F (24 ^o C)
Recoat time	6-8 hours @ 75 ^o F (24 ^o C)
'Open' to foot traffic	12-16 hours @ 75 ^o F (24 ^o C)
'Open' to vehicle traffic	36+ hours @ 75 ^o F (24 ^o C)
Shelf Life	6 months in unopened unit

For physical properties on this product, refer to ROCK-TRED's Data Chart

PACKAGING:

- 2.5 Gallon Units

ELASTI-THANE BASECOAT

LIMITATIONS & FOR BEST RESULTS:

- Do not thin this product.
- Do not apply when work area exceeds 70% relative humidity or when substrate temperatures may fall to less than 5° F above dew point during the curing of the material.
- Apply the next coat within 24 hours of completing the previous coat.
- Do not apply this product heavier / thicker than the recommended spread rate / mil thickness.

PRODUCT APPLICATION:

Apply using brush, roller and squeegee ROCK-TRED product test data is based on environmental temperatures of 75° F (24° C). Viscosity and working time are always affected by temperatures above or below that mark. When applying product – **always consider the ambient, surface, and product temperature at the time and place of installation.**

COLOR AND TEXTURES:

ELASTI-THANE BASECOAT is available in gray, black, and white. Most ROCK-TRED products are available in a wide range of textures using an appropriate aggregate.

CHEMICAL RESISTANCE:

Always refer to ROCK-TRED's chemical resistant chart for specific information on each product / system or contact ROCK-TRED directly.

PRODUCT STORAGE:

DO NOT allow ROCK-TRED products to freeze. All ROCK-TRED products should be properly stored above the floor on pallets or shelves, and in an area that has a constant minimum temperature of 50° F (10° C).

SURFACE PREPARTION: Always apply ROCK-TRED products to a clean / sound substrate that is free of laitance, grease, oils, debris, and curing compounds. Concrete substrates should be cured for a minimum of 28 days prior to application of product [except as otherwise noted on the individual Product Data Sheet]. Whenever possible, remove existing coatings and/or flooring systems completely; if complete removal is not possible always perform tests to determine adhesion and compatibility to the existing flooring. Surface preparation by means of a shot-blasting machine is the best and recommended method for attaining the desired profile. If the substrate is not properly prepared and the appropriate profile is not achieved, failure of the product to adhere to the substrate may occur.

CLEAN UP:

Application tools and equipment can be cleaned with xylene immediately after use.

DISPOSAL:

Product containers will contain product residue and must be disposed of properly. Label warnings must be observed at all times. All containers must be disposed in accordance with federal, state, and local regulations.

IMPORTANT NOTICE:

Always read and acquaint yourself with ROCK-TRED'S Product Data Sheet, MSDS [material safety data sheet], and product labels for each individual product prior to mixing and prior to use. For further assistance, product questions, additional information and/or unexpected or unusual installation conditions – contact your local representative or ROCK-TRED directly for recommendations.

WARRANTY:

Information about ROCK-TRED products is given, to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you make your own tests to determine suitability of the product for the particular purpose. As products are often applied or used under conditions beyond our control, ROCK-TRED cannot guarantee anything except the quality of its products. ROCK-TRED warrants that the products meet the specifications set forth by ROCK-TRED, but we reserve the right to change any given specification prior to notice. ROCK-TRED DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of a ROCK-TRED product constitutes acceptance of the terms of this limited warranty and the terms and conditions set out in our invoice, contrary provisions of buyer's purchase documents notwithstanding. Upon receipt of the merchandise, purchaser has 30 days to notify ROCK-TRED, in writing, that materials are defective. In the event ROCK-TRED finds that the product delivered is off specification, ROCK-TRED will, at its sole discretion, either replace the product(s) or refund the purchase price thereof, and ROCK-TRED's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of ROCK-TRED exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. ROCK-TRED will, under no circumstance, be liable for special, incidental, or consequential damages. This warranty supersedes all other guarantees, whether oral or written, and whether expressed, implied, or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using, please read the Material Safety Data Sheet and follow all precautions to prevent bodily harm.