

TECHNICAL DATA  
**RT SERIES 402**  
**CHEM-ROCK MV**

**100% SOLIDS EPOXY MEDIUM VISCOSITY BUILD AND FINISH COAT**

TECH DATA SHEET CHEM-ROCK MV RT SERIES 402

**DESCRIPTION:**

**CHEM-ROCK MV** is a water clear, 100% solids, medium viscosity, 2-component, cyclo-aliphatic epoxy coating. **CHEM-ROCK MV** is a multi-use coating designed to provide very good abrasion and chemical resistance, UV protection, gloss retention, durability and workability for the applicator.

**USES:**

**CHEM-ROCK MV** is used where a water clear or solid color high build neat coating is required or as an easy working, self-leveling body or finish coat in broadcast or trowel applied industrial and decorative flooring systems. Its medium viscosity characteristic makes it an ideal "seed" coating to broadcast flakes or aggregate into. **CHEM-ROCK MV** meets USDA/FDA guidelines for use in federally inspected facilities and all VOC/HAPS regulations for use throughout the United States.

**TYPICAL COVERAGE:**

**CHEM-ROCK MV** is typically applied between 60-150 square feet per gallon per coat depending upon substrate and project requirements.

**ADVANTAGES:**

- 100% solids
- Faster cure available using CHEM-ROCK Accelerator
- Able to be field pigmented
- Excellent inter-coat adhesion to ROCK-TRED primers and finish coats
- Medium viscosity, high building material
- Water-clear, high gloss finish
- Easy mix ratio
- Good UV and chemical resistance

**TYPICAL PROPERTIES:**

PHYSICAL PROPERTIES	
Volume mix ratio	2 to 1 (Resin to Hardener)
Viscosity (mixed)	900-1000 CPS Typical
Solids Content (%)	100% (ASTM D-2697)
Hardness (ASTM D-2240)	75 - 85 (Shore D)
VOC	Compliant with all US Regulations
Application Temps.	60° – 85°F
Gel Time	40-50 minutes @ 75°F
Dry to Touch (recoat with compatible products)	3 - 4 hours @ 75°F
Through Cure	8 - 10 hours @ 75°F
Open for light traffic	24 hours @ 75°F
Shelf Life	1 Year in unopened units

**PACKAGING:**

- 1.5 Gallon BAG-PAK™ Unit in a single pail
- 3 Gallon BAG-PAK™ Unit in a single pail
- 15 Gallon Unit in three 5 gallon pails
- 165 Gallon Bulk Unit in three 55 gallon drums

# RT SERIES 402 CHEM-ROCK MV

## LIMITATIONS & FOR BEST RESULTS:

- Do not thin this product.
- Do not apply when Humidity exceeds 70% indoors.
- Do not allow to puddle during application.
- Allow each coat to dry to 'tack-free' or clear prior to re-coat.
- When re-coating, always apply the next coat within 24 hours of completing the previous coat.
- When pigmenting this product using lighter colors application at 15 mils or in multiple coats may be required for full hide.

## PRODUCT APPLICATION:

Apply using brush, roller and squeegee ROCK-TRED product test data is based on environmental temperatures of 75°F. Viscosity and working time are always affected by temperatures above or below that mark. When applying product always consider the ambient, surface, and product temperature at the time and place of installation.

## COLOR AND TEXTURES:

**CHEM-ROCK MV** is manufactured in water clear and can be field pigmented using ROCK-TRED colorants. Most ROCK-TRED products are available in a wide range of textures using an appropriate aggregate.

## CHEMICAL RESISTANCE:

Always refer to ROCK-TRED's chemical resistant chart for specific information on each product / system or contact ROCK-TRED directly.

## PRODUCT STORAGE:

**DO NOT** allow ROCK-TRED products to freeze. All ROCK-TRED products should be properly stored above the floor on pallets or shelves, and in an area that has a constant minimum temperature of 50°F.

## CLEAN UP:

Application tools and equipment can be cleaned with soap and water immediately after use, or with solvent once the product has begun to cure.

**SURFACE PREPARATION:** Always apply ROCK-TRED products to a clean / sound substrate that is free of laitance, grease, oils, debris and curing compounds. Make certain that concrete is properly dried and prepared before applying ROCK-TRED materials. Concrete substrates should be treated with ICP's Arizona Polymer Flooring System's Vapor Solve System when moisture testing per ASTM F2170 shows results over 80% RH. Whenever possible, remove existing coatings and/or flooring systems completely; if complete removal is not possible test to determine adhesion to the existing material. Mechanical preparation by means of shot-blasting or diamond grinding to a ICRI CSP 2/3/5 is the recommended preparation method (see ICRI Guideline No. 03732 for more information). If the substrate is not properly prepared and the appropriate profile is not achieved, failure of the product to adhere to the substrate may occur.

## DISPOSAL:

Product containers will contain product residue and must be disposed of properly. Label warnings must be observed at all times. All containers must be disposed in accordance with federal, state, and local regulations.

## IMPORTANT NOTICE:

Always read and acquaint yourself with ROCK-TRED's Product Data Sheet, SDS [safety data sheet], and product labels for each individual product prior to mixing and prior to use. For further assistance, product questions, additional information and/or unexpected or unusual installation conditions – contact your Area Sales Representative or ROCK-TRED directly for recommendations. Kit components are pre-measured for optimal performance. Catalyzation errors due to incorrect mixing in the field.

**WARRANTY:** Information about ROCK-TRED products is given, to the best of our knowledge, based on tests and experience. Such information supplied about our products is not a representation or a warranty. It is supplied on the condition that you make your own tests to determine suitability of the product for the particular purpose. As products are often applied or used under conditions beyond our control, ROCK-TRED cannot guarantee anything except the quality of its products. ROCK-TRED warrants that the products meet the specifications set forth by ROCK-TRED, but we reserve the right to change any given specification prior to notice. ROCK-TRED DISCLAIMS ALL WARRANTIES RELATING TO THE PRODUCTS AND THEIR APPLICATION, EXPRESS OR IMPLIED, INCLUDING BUT NOT LIMITED TO THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE. Receipt of a ROCK-TRED product constitutes acceptance of the terms of this limited warranty and the terms and conditions set out in our invoice, contrary provisions of buyer's purchase documents notwithstanding. Upon receipt of the merchandise, purchaser has 30 days to notify ROCK-TRED, in writing, that materials are defective. In the event ROCK-TRED finds that the product delivered is off specification, ROCK-TRED will, at its sole discretion, either replace the product(s) or refund the purchase price thereof, and ROCK-TRED's choice of one of these remedies is the buyer's sole remedy. In no event shall the liability of ROCK-TRED exceed the purchase price of shipped merchandise. Claims must be in writing. Claims after 30 days are void. ROCK-TRED will, under no circumstances, be liable for special, incidental, or consequential damages. This warranty supersedes all other guaranties, whether oral or written, and whether expressed, implied, or statutory. No representative is authorized to make any representation or warranty or assume any other liability on our behalf with any sale of our products. Certain products may contain chemicals that may cause serious physical injury. Before using, please read the Safety Data Sheet and follow all precautions to prevent bodily harm.